



VENEER MORTAR

	FOR RICK NEERS IG 2PERSON	SET TIME 1-2 HRS IN 28 DAYS B MPa	AVAILABLE SIZE: 30KG
YIELD PER 30KG BAG VOLUME	BRICKS 230 X 76 X 70mm 42-48	BRICKS 230 X 119 X 70mm 33-38	BRICKS 290 X 75 X 70mm 32-36
0.016m³ This table has been calculated on the brick size as stated and should be used as a guide only.	BRICKS 230 X 90 X 75mm 33-38	BRICKS 290 X 160 X 70mm 41-46	BRICKS 390 X 190 X 90mm 18-24

Dricon[®] Veneer Mortar is specially designed for brick veneer mortar jobs. It consists of a uniformly blended mixture of graded sands, EcoSure Low Carbon Cement and specialised admixtures for a high level of workability and coverage. Endorsed by the Brick and Blocklayers Federation, Veneer Mortar works just like Dricon[®] Trade Mortar but gives you the option for a lower MPa product to meet brick veneer installations. Dricon[®] Veener Mortar is grey in appearance but can be coloured using selected Dricon[®] Oxitone[®] Oxides. It can also be further enhanced by using Dricon[®] Concrete Treatment.

COMPRESSIVE STRENGTH

8MPa after 28 days.

WATER CONTENT

4.2 - 4.8 litres per bag

EQUIPMENT

Veneer Mortar is designed to be mixed in a concrete mixer and applied with a mason's trowel.

JUST ADD WATER

Pour 4.2 to 4.8 litres of water into the mixer then slowly add the bag of Veneer Mortar (water quantities will vary according to seasonal conditions and outside temperature, however, ensure that the water ratio for the given job at hand remains constant from bag to bag).

MIXING

Allow 5-6 minutes of mixing time to get the correct Veneer Mortar consistency.

TEST YOUR MIX

To test, scoop Veneer Mortar onto trowel, tap the bottom of trowel on hard surface then turn upside down. The Veneer Mortar should stick to the trowel.

LAYING

The board life of Veneer Mortar under normal weather conditions is on average 30-35 minutes.

SUITABLE PROJECTS

- Brick Veneer
- Roof Bedding


BENEFITS

- Minimises waste
- Has consistent material calculations from bag to bag

ENDORSED BY

Master Brick & Blocklayers

- Contains a dry plasticiser accepted and endorsed by key trade users
- 30kg bag size for ease of use
- Lower strength option to meet brick
 veneer installation





VENEER MORTAR

DRICON® TECHNICAL DATA SHEET



PRODUCT INFORMATION

PACKAGING	Paper bag
SIZE	30kg
SHELF LIFE	12 Months from date of production
STORAGE	Keep in dry location free of moisture
COLOUR	Grey
GRAIN SIZE	Up to 2.5mm
WATER DEMAND PER KG	0.14 to 0.16 litres
WET DENSITY	Approximately 1750 kg/m³
WORK TIME	30-35 minutes
INITIAL SET TIME	1-2 hours
APPLICATION THICKNESS	No less than 5mm
APPLICATION TEMPERATURE	5 to 30°C
COMPRESSIVE STRENGTH 7 DAY	> 5 MPa
COMPRESSIVE STRENGTH 28 DAY	> 8 MPa
FLEXURAL STRENGTH	Approximately 340 kPa (red clay brick)
SAFETY INFORMATION	Refer to the Safety Data Sheet on our website

GENERAL INFORMATION

If only part of the bag is required, mix the entire contents of the bag together first in a dry state, return the unwanted portion to the bag or alternatively a dry sealed container, then follow the instructions.

All mortars and concrete products may exhibit a temporary 'whitening', otherwise known as efflorescence which neither affects strength nor durability.